ULTRATEC Coatings System

PRODUCT NAME	ULTRATEC TOPCOAT
Color	Solids, Metallic, Mica & Effect finishes
Туре	Water Based
Components	Single component
Viscosity: (ASTM D 2196-86)	80 to 100KU (30°C)
Specific Gravity (ASTM D 1475-90)	1.15 -1.45 (depending on colour)
Gloss @60° (ASTm D523)	10-20 (Eggshell), 30-45 (Semi-gloss)
Accelerated Weathering (QUV)	6000hrs
SRI (ASTM E1980-11)	91
рН	8.5-9.5
Solids	40% to 55%
VOC (BS EN ISO 11890-1:2007)	20-30g/l
Volume Solids	35% to 40%
Recommended Film thickness	100 to 150 Wet; 40 to 60 Dry
Coverage	350-400/Sqm/Litre/Microns
Dry Time	Touch dry - 15 to 30 min; Recoating-18-24 hrs
Shelf Life	12 months under Shed at 25°C